







LIPID BASED COMPOSITION CONTAINING DIACYLGLYCEROL, PHOSPHOLIPID, POLAR LIQUID AND BIOLOGICALLY ACTIVE MATERIAL

Publication number: WO9534287 (A1)	Also published as:
Publication date: 1995-12-21	 US5807573 (A)
Inventor(s): LJUSBERG-WAHREN HELENA [SE]; LARSSON KAARE [SE] +	 SE9402106 (L)
Applicant(s): GS DEV AB [SE]; LJUSBERG WAHREN HELENA [SE];	 SE518578 (C2)
LARSSON KARE [SE] +	 NO965380 (A)
Classification:	 JP10504532 (T)
- international: A61K47/14; A61K9/107; A61K9/127; A61K47/14; A61K9/107; A61K9/127; (IPC1-7): A61K9/00; A61K9/127	more >>
- European: A61K9/127K	
Application number: WO1995SE00593 19950524	Cited documents:
Priority number(s): SE19940002106 19940615	 WO8402076 (A1)

Abstract of WO 9534287 (A1)

A biologically active composition containing (a) a diacyl glycerol, (b) a phospholipid and, optionally, (c) a polar liquid in such proportions that they together form an L2-phase or a cubic liquid crystalline phase, in which a biologically active material is dissolved or dispersed. A method for preparing the composition by mixing (a), (b) and, optionally, (c) for forming an L2-phase or a cubic liquid crystalline phase, the biologically active material being added before, during or after the formation of said phase. Use of the L2-phase or the cubic liquid crystalline phase for encapsulating a biologically active material for obtaining a preparation, which yields a controlled release of the biologically active material.

Data supplied from the *espacenet* database — Worldwide



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/127, 9/00	A1	(11) International Publication Number: WO 95/34287 (43) International Publication Date: 21 December 1995 (21.12.95)
<p>(21) International Application Number: PCT/SE95/00593</p> <p>(22) International Filing Date: 24 May 1995 (24.05.95)</p> <p>(30) Priority Data: 9402106-0 15 June 1994 (15.06.94) SE</p> <p>(71) Applicant (for all designated States except US): GS DEVELOPMENT AB [SE/SE]; Jägershillsgratan 15, S-213 75 Malmö (SE).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): LJUSBERG-WAHREN, Helena [SE/SE]; Gränsvägen 18B, S-236 33 Höllviken (SE). LARSSON, Kåre [SE/SE]; N Villavägen 7B, S-237 34 Bjärred (SE).</p> <p>(74) Agent: AWAPATENT AB; P.O. Box 45086, S-104 30 Stockholm (SE).</p>		<p>(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: LIPID BASED COMPOSITION CONTAINING DIACYLGLYCEROL, PHOSPHOLIPID, POLAR LIQUID AND BIOLOGICALLY ACTIVE MATERIAL</p> <p>(57) Abstract</p> <p>A biologically active composition containing (a) a diacyl glycerol, (b) a phospholipid and, optionally, (c) a polar liquid in such proportions that they together form an L2-phase or a cubic liquid crystalline phase, in which a biologically active material is dissolved or dispersed. A method for preparing the composition by mixing (a), (b) and, optionally, (c) for forming an L2-phase or a cubic liquid crystalline phase, the biologically active material being added before, during or after the formation of said phase. Use of the L2-phase or the cubic liquid crystalline phase for encapsulating a biologically active material for obtaining a preparation, which yields a controlled release of the biologically active material.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Lipid based composition containing diacylglycerol,
phospholipid, polar liquid and biologically active
material

Technical Field

The present invention relates to the field of polar lipids and, more specifically, to a new biologically active composition, which is based on polar lipids and
5 has been found to yield significant improvements as compared with previously known lipid-based compositions used as carriers for biologically active materials. More concretely, the invention relates to a new composition whose L2-phase and cubic liquid crystalline phase each confer
10 advantages in the controlled release of biologically active material encapsulated therein, as compared with previously known, similar L2-phases and cubic phases, respectively, and are mutually positioned in a phase diagram so as to also confer valuable advantages for some
15 specific applications in which special demands are placed on the release of biologically active materials.

Background of the Invention

Polar lipids are amphiphilic molecules, i.e. they are both "hydrophilic" and "hydrophobic". When placed in
20 an aqueous solution, they must thus unite in some way or another to form different kinds of aggregates. The most well-known of the aggregates formed in water is probably the spheric micelle, which typically contains 50-100 lipid molecules arranged in such a manner that their
25 hydrocarbon tails (the hydrophobic part) form the interior of the micelle concerned and the polar main groups (the hydrophilic part) act as a shield against the surrounding water.

The micelle, however, is only one of many different
30 types of aggregate formed. It is also possible to find both bar-shaped micelles and reversed-type micelles (L2), which are also called microemulsions in which water forms the internal phase.

A number of liquid crystalline structures are also
35 normally found in systems of polar lipid and water. These

comprise hexagonal phases of the normal type (HI) and of the reversed type (HII), as well as the lamellar phase ($L\alpha$). The lamellar structure provides, at an excess of water, liposomes, which are spheroidal shells of lipid bilayers. These have been studied to a very large extent and have been used in the release of pharmaceutical preparations, for example in chemotherapy of cancer. The first liposome product on the market contains amphotericin and is intended for treatment of infections.

Many cubic crystalline phases are said to be both water- and oil-continuous, i.e. bicontinuous. These phases consist of lipid bilayers whose centre forms a minimum surface, separating two water channel systems. There are four main positions in the phase diagram, in which cubic phases can be found. Cubic phases of normal topology (oil-in-water) can be found either adjacent the micellar solution (in many cases between the normal micellar solution ($L1$) and the hexagonal HI-phases), or between the HI-phase and the lamellar $L\alpha$ -phase. In the first-mentioned case, the structures are considered to be anisotropic micellar aggregates. In the last-mentioned case, the structures seem to be permanently bicontinuous. Cubic phases may also be found between the $L\alpha$ - and the HII-phase. In this case, the structures are also bicontinuous. Cubic liquid crystalline phases occurring in the fourth possible position in the phase diagram, i.e. between the HII-phase and the reverse micellar solution ($L2$), have been studied by J.M. Seddon in Biochemistry, Vol. 29, No. 34, 1990, pp 7997-8002, and by V. Luzzati et al, in Biochemistry 1992, 31, pp 279-285, but these articles do not concern the properties which these phases have been found to possess in the release of biologically active materials.

Furthermore, certain compositions are per se known, whose $L2$ -phase, hexagonal phase and/or cubic phase (formed when mixing water and amphiphilic lipids) have been used for the release of biologically active materials. As

examples of publications illustrating this, mentioned can be made of US 4,388,307, US 5,143,934, US 5,151,272, US 5,196,201, US 5,262,164, EP,B1, 314,689, WO 92/20377 and the article by T. Norling et al. in J. Clin. Periodontol 5 1992, 19, pp 687-692. This does not correspond to the composition of the L2-phase and the cubic phase for the composition according to the present invention, the mutual positioning of the two phases or their advantageous properties in the controlled release of biologically 10 active materials.

Summary of the Invention

According to the present invention, a new composition is provided, which is so made up and has such properties that there are a number of advantages as compared with the 15 previously known compositions within this field. Thus, it has surprisingly been found that the biocompatibility of a composition according to the invention is better than that of the previously known compositions of this type based on monoglycerides (monoacyl glycerol). Besides it has been un- 20 expectedly found that the release profile of the biologically active material from the composition according to the present invention is more advantageous than that of the previously known glyceride-based compositions used for this purpose. In addition to this, the L2-phase and the cubic 25 phase have such a mutual positioning in a phase diagram that the L2-phase may be used for specific applications of a biologically active material in situ in mammals, especially humans, by the L2-phase swelling when contacting body fluid or added polar liquid, such that a phase transi- 30 tion to the corresponding cubic liquid crystalline phase occurs. In practice, this means that a casting in situ can be accomplished in the specific position in which the application of the biologically active material is desired.

A first object of the invention thus is to provide a 35 lipid composition, which yields a controlled release of a biologically active material encapsulated therein.

A further object of the invention is to provide a lipid composition, which has improved biocompatibility compared with previously known glyceride-based systems.

One more object of the invention is to provide a
5 composition, which yields an enhanced release profile for a biologically active material as compared with previously known monoacyl-glycerol-based systems.

One more object is to provide a lipid composition, in which the carrier of the biologically active material
10 is biodegradable.

A still further object of the invention is to provide a lipid composition, for which the phase transition from the L2-phase to the cubic liquid crystalline phase can be used to "cast" the desired biologically active material in situ where the intended effect should occur.
15

Other objects and advantages of the invention will be apparent to those skilled in the art from the following, detailed description of the invention.

The objects of the invention are achieved by a glycerol-ester-based composition comprising
20

(a) at least one diacyl glycerol, wherein the acyl groups, which are the same or different, are each derived from an unsaturated fatty acid having 16-22 carbon atoms, or from a saturated fatty acid having 8-10 carbon atoms,

25 (b) at least one phospholipid selected from glycerophosphatides and sphingophosphatides, wherein the acyl groups, which are the same or different, are each derived from a fatty acid having 14-22 carbon atoms, and

optionally, (c) at least one polar liquid selected
30 from the group consisting of water, glycerol, ethylene glycol and propylene glycol,

the proportions between the components (a), (b) and optionally (c) being such that they together form an L2-phase or a cubic liquid crystalline phase, wherein (c) is
35 an optional component in the case of L2-phase and a requisite component in the case of cubic liquid crystalline phase, and the biologically active material being

dissolved or dispersed in said L2-phase or said cubic liquid crystalline phase.

In general, the unsaturated fatty acid for the diacyl glycerol (a) should be liquid at room temperature and it should preferably contain 16-20 carbon atoms. A particularly advantageous fatty acid in this context is one having 18 carbon atoms. Of these fatty acids having 18 carbon atoms, oleic acid and linolic acid are of special interest, and oleic acid is the one most preferred. Diacyl glycerol (a) from saturated fatty acids in liquid state implies, however, that the chain length of the fatty acid is shorter, for example 8 or 10 carbon atoms. So-called medium chain length triglycerides may be used as starting material for the preparation.

In many cases it is, however, not necessary to use or even, if anything, preferred from the economical point of view not to use the diacyl glycerol in pure or synthesised form, but to use a natural product containing essentially the same, for example in which the desired diacyl glycerol is obtained by esterification/reesterification between glycerol and vegetable or animal oils or fatty acids therefrom. Preferred examples of such oils are canola, maize, cottonseed, olive, rape-seed, soybean, safflower, sunflower, linseed and tall oil.

The used phospholipid is, as mentioned above, generally based on a fatty acid having 14-22 carbon atoms. A preferred carbon atom content of said fatty acid is, however, 16-20, while 16 or 18 carbon atoms are especially preferred. Also in this case, a phospholipid derived from a natural product in the form of vegetable or animal raw materials may, however, also be concerned. Examples of preferred such raw materials are soybean, rape-seed and egg.

However, the phospholipid may of course also be an entirely synthetic product.

As preferred examples of glycerophosphatides, mention can be made of lecithines and cephalines which are based

on choline and, respectively, ethanolamine or serine. Especially preferred is phosphatidyl choline. An especially preferred sphingophosphatide is sphingomyelin which is also based on choline. Specific examples of phospholipids
5 are dioleoylphosphatidyl choline and dioleoylphosphatidyl ethanolamine.

In respect of the unsaturated fatty acid for the diacyl glycerol (a), the term "unsaturated" includes both monounsaturated and polyunsaturated, i.e. said acid can
10 contain one or more unsaturated valences.

The fatty acid for the phospholipid (b) can be saturated, monounsaturated and/or polyunsaturated. A saturated fatty acid of special interest is one having 16 carbon atoms, while a monounsaturated fatty acid of special
15 interest is one having 18 carbon atoms.

The polar liquid used in the inventive composition is preferably water, but this water may also be wholly or partially replaced with another polar liquid, such as glycerol, ethylene glycol and/or propylene glycol. The
20 release rate of the biologically active material may thus be, for example, adjusted by varying the proportions of the used polar liquids. By water is meant not only pure water, but of course also, for instance, an isotonic aqueous solution or a body fluid, especially in the case
25 of casting in situ in or on the tissue of humans or animals.

The exact composition of the L2-phase and/or the cubic liquid crystalline phase is, of course, taken from a phase diagram, and the desired release rate of the biologically active material which is to be encapsulated is
30 readily determined by a person skilled in the art by simple routine testing. The enclosed figure illustrates, as will be described in more detail below, the phase diagram for a specific system within the scope of the present
35 invention, which means that the exact composition of the L2-phase and/or the cubic phase can be taken from this diagram for exactly this specific system. Since the

inventive idea has now been presented, the expert will probably have no difficulties in preparing the corresponding phase diagram for other specific systems within the scope of the invention and determining the exact position of the desired L2-phase and/or cubic phase.

However, it may be generally said that the weight ratio of diacyl glycerol:phosphatidyl choline is in the range from 95:5 to 50:50, preferably from 90:10 to 70:30.

The weight content of the polar liquid (c), based on the total weight of (a) plus (b) plus (c), is generally in the range of 0-20%, especially 0-15%, such as 0-10% for the L2-phase and 5-15% for the cubic phase. Thus, in the case of L2-phase, the content of the polar liquid (c) may even be 0, i.e. even the diacyl glycerol and the phospholipid mixed together may give the desired L2-phase. In many cases, it is however the matter of a certain content of polar liquid in the L2-phase, and in the cubic liquid crystalline phase, said liquid is of course always present. Small amounts of water may also be bound to the phospholipid and, thus, be added via the phospholipid.

As indicated above, an especially preferred embodiment of the inventive composition is represented by the case in which the cubic liquid crystalline phase is obtained by swelling of the corresponding L2-phase with the polar liquid. Of course, this means in such a case that the L2-composition is selected such that the adding of the stated liquid, e.g. body fluid, yields a phase transition from the L2-phase to the cubic liquid crystalline phase. Other phase transitions are, however, also within the scope of the invention, if desired. In some cases, a reversed hexagonal phase can be formed in addition to the cubic phase.

By the above-mentioned phase transition, the cubic liquid crystalline phase can be cast in situ where the desired controlled release of the biologically active material is wanted. The enormous advantages this may confer in some specific cases for application of special medical

preparations for achieving, for instance, a local effect, will be easily understood by the expert.

The invention is not restricted to one or a few specific biologically active materials, but is generally
5 applicable to the different types of biologically active materials which have been present earlier in similar contexts. However, it will be easily realised that new fields of application for certain types of medical preparations will open up by means of the present invention,
10 especially when using the phase transition L2 to cubic phase. By "biologically active material" or the like is, in the present case, like before, meant a compound or composition which, when present in an effective amount, reacts with and/or affects living cells and organisms.
15 This includes also a biological material which requires a controlled release for vaccination purposes. Preventing the release of medicals having a bad taste is a further application of the invention.

An interesting group of compounds for encapsulation
20 according to the present invention is, however, the group of pharmaceutical compounds, such as antibiotics, antimycotics, proteins, peptides, steroids, local anesthetics, chemotherapeutants and antiviral substances.

Whether the biologically active material is dis-
25 solved or dispersed depends, of course, on its solubility in the phase mentioned, i.e. whether it is water-soluble, lipid-soluble etc, but to this part of the invention, the prior art technique applies, as well as to where in the phase concerned the resolution/dispersion takes place in
30 reality.

The content of the biologically active material is of course dependent on a number of different factors which are well-known to the expert, especially the desired degree of activity. The content must therefore be
35 determined by the expert in each individual case. However, it may be generally said that the biologically active material is present in an amount of 0.01-30%,

especially 0.1-5% for soluble substances, and 5-30% for a dispersion, the percentages being expressed as percent by weight based on the weight of the total composition.

The biologically active composition is, as indicated
5 above, of special interest as pharmaceutically acceptable composition. Of course, this also means that it is prepared in a conventional manner for the desired administration.

Examples of specific applications in which the biologically active composition according to the present invention may be used are

when administering antibiotics (e.g. tetracycline, metronidazole), for example when treating parodontosis;
for enhancing the absorption of proteins/peptides
15 (e.g. cyclosporins);

when treating infections in and adjacent mucous membranes;

in parenteral administration of drugs, especially via the L2-phase (for example vaccine), and
20 in depot preparation for e.g. steroids or antibiotics.

However, these applications are in no way restrictive to the invention, since this is primarily directed to new carriers for active substances, and not to the substances as such.
25

According to another aspect of the invention, a method is provided for preparing the above described composition, the method comprising the steps of mixing the diacyl glycerol (a), the phospholipid (b) and, optionally, the polar liquid (c) in such amounts that an L2-phase, alternatively a cubic liquid crystalline phase, is formed, the mixing procedure for providing said L2-phase or said cubic liquid crystalline phase occurring according to per se known principles, which need not be described here.
35

The addition of the biologically active material is carried out before, during or after the formation of said

L2-phase or said cubic liquid crystalline phase. Regarding the addition of the active material to said phase "before" the formation thereof, it should also be said for the sake of clarity that this means of course that
5 the material can be added from the beginning to one of the components (a), (b) or (c), before they are in turn mixed for obtaining the desired L2-phase or cubic phase.

Besides, according to that described above, the cubic liquid crystalline phase is possibly formed in the
10 position in which the controlled release of the biologically active material is desired, viz. by the presence or addition of the polar liquid (c), for example in the form of body fluid.

Moreover, the preferred embodiments which have been
15 described above in connection with the inventive composition apply to the method according to the invention.

Finally, the invention also relates to the use of an L2-phase or a cubic liquid crystalline phase according to the above definitions for encapsulating a biologically
20 active material for obtaining a preparation, which yields a controlled release of the biologically active material. Such a preparation can also imply that the lipid-based composition is dispersed in an aqueous solution by prior art technique.

25 Also in respect of the use, the preferred embodiments are those described in more detail above.

It may also be added that in the present case, the term "biocompatibility" has the generally recognised meaning "ability of a material to give a biologically
30 acceptable, or good, response in a host organism in a specific application. More concretely, the lipid mixture must not cause undesirable tissue reactions in the form of infection, inflammation or other rejection phenomena. Examples of undesirable reactions are swelling, pain or
35 the formation of connective tissue capsules. It is also important that the lipid mixture affects the inherent healing power as little as possible, i.e. such that the

natural healing process is not disturbed or affected to any decisive degree.

Description of the Drawing

The enclosed drawing figure illustrates a ternary
5 diagram of the specific system diacyl glycerol from sunflower oil, phosphatidyl choline from soybean and water at 25°C. In this drawing figure, the symbols have the following meanings:

- A = diacyl glycerol
- 10 B = phospholipid
- C = polar liquid
- D = L2-phase, and
- E = cubic liquid crystalline phase.
- Moreover, this phase diagram shows:
- 15 F = hexagonal, and
- G = lamellar liquid crystalline phase.

Examples

The present invention will finally be further illustrated by means of the following working examples regarding
20 the preparation of some specific compositions according to the invention and their properties in the release of biologically active material.

EXAMPLE 1

Phospholipid in the form of a purified soybean phosphatidyl choline (about 95%) and diacyl glycerol derived
25 from sunflower oil and containing 80% oleic acid, based on the total fatty acid content, were weighed in the ratio of 15:85 in an injection bottle (10 ml), which was filled with inert atmosphere and sealed. The sample was
30 allowed to assume equilibrium at room temperature and was centrifuged back and forth, thereby providing a homogeneous mixture of the components. The L2-phase was formed in the form of a homogeneous, mobile oil.

EXAMPLE 2

35 1 g of the L2-phase prepared according to Example 1 above was transferred to a test tube, which was centrifuged such that all the material was obtained on the bottom.

9 g of an aqueous solution of Pluronic F68 (1.1 weight/-
weight BASF) were added to the test tube. The sample was
treated with an ultrasonic rod (Branson sonifier 250,
microtip) for 1+2 min at a power of 52 W + 56 W. A stable,
5 milky emulsion was formed in this treatment of the two
phases in the sample.

EXAMPLE 3

A fine-grain powder of metronidazol benzoate (7% by
weight) was mixed with the L2-phase prepared from the
10 above-mentioned phosphatidyl choline and diacyl glycerol
in the ratio of 3:7. The dispersion was of relatively low
viscosity, but when adding water to the dispersion, the
sample solidified.

The particle dispersion of metronidazol benzoate in
15 the L2-phase was studied under microscope, magnified 200
times. This study showed that the particles were well
dispersed without any formation of aggregates.

EXAMPLE 4

The biocompatibility and the biodegradability of
20 liquid crystalline phases, which may function as depot
preparations for drugs, were studied in a so-called abdo-
men plug model on rat. The model is developed for testing
implant material, for example plastics, but has also
appeared to function satisfactorily for the evaluating of
25 depot preparations. This model means that the material to
be studied is inserted between the straight abdominal
muscle and the peritoneum in male rats (Sprague-Dawley,
350-400 g).

The samples studied were obtained from soybean phos-
30 phatidyl choline and sunflower oil glycerides. The lipids
were first swelled with a physiological salt solution to
liquid crystalline phases, which were implanted. These
liquid crystalline phases can be in equivalence with an
excess of water and are suitable for testing in this
35 model.

The animals were put to death after 10 and 30 days, and the size of the connective tissue capsule and the amount of residual sample were noted.

5 The thickness of the capsule may be taken as a measure of the biocompatibility of the material. The results after 10 days are summarised in the table below. The measure of the capsule thickness is relative and concerns the number of squares in the microscope.

10 After 30 days, all lipid implants had decreased in size or disappeared completely, which proves that the lipids are biodegradable.

<u>Lipid</u>	<u>Capsule thickness</u>
monoacyl glycerol	2.0
phospholipid/diacyl glycerol 1:1	0.4*

15 * the capsule was partly fragmented.

EXAMPLE 5

Biodegradable systems for the controlled release of bioactive systems should have a degradation profile which conforms with the release, since otherwise an empty carrier, which serves no purpose, may remain in the tissue. This is especially the case with water-soluble substances, which are released by diffusion. Therefore, a study was made of the effect of water on particles of a water-soluble colourant (methylene blue) which was dispersed in
20 two different lipid carrier systems.

Particles of methylene blue were thus mixed with two different L2-phases, viz. a first one from the system monoacyl glycerol (sunflower oil)/water and a second one from the system phospholipid/diacyl glycerol from Example
30 3. Both L2-phases formed a highly viscous cubic liquid crystalline phase at an excess of water. In the first case, the cubic phase was both water- and oil-continuous, whereas the cubic phase formed in the latter case was oil-continuous only.

35 The samples were studied under microscope, magnified 200 times, after addition of water, and the following phenomena were noted:

14

a distinct release of methylene blue from the dispersion to water occurred from the monoacyl-glycerol-based system. The dispersion of methylene blue in the L2-phase of diacyl glycerol/phospholipid demonstrated no such release, when an excess of water was present.

The release of drugs from the system phospholipid/-diacyl glycerol can, consequently, be assumed to be controlled more by the degradation shown in vivo in Example 4 than by diffusion, whereas the release of drugs from a liquid crystalline phase based on monoglyceride will be more difficult to control, since this is more dependent on the properties of the pharmaceutical preparation, such as molecular size and solubility.

EXAMPLE 6

In this example a dispersion of a local anesthetic was prepared by dispersing a fine powder of lidocaine hydrochloride in a liquid 33:67 mixture of phosphatidyl choline from soy and diacyl glycerol from tall oil to an L2-phase containing 40% by weight of lidocaine-HCl. The dispersion was relatively mobile and was sprayable. The preparation solidified when sprayed into water and a sustained dissolution of the lidocaine-HCl crystals was obtained as compared with the case when said crystals were directly mixed with water.

EXAMPLE 7

Cytotoxicity tests were performed in the following way. Two liquid crystalline phases having cubic structures but different compositions were tested in a way that is utilized in the biomaterial field (ISO 10993-5:1992(E)) to test whether plastic materials release anything that is toxic to cells. Both these cubic phases can be in equilibrium with water without being dispersed and can thus be tested as solid bodies.

Samples from the cubic phases having an area of 3,14 cm² were contacted with water (4 ml) at 37°C for more than 24 hours. The aqueous phase was then separated from the

15

cubic phase and admixed with growth media to which a cell culture was added. The evaluation was then performed with reference to growth inhibition of fibroblasts.

The results were as follows:

Composition of cubic phase		Growth inhibition
Monoolein* from tall oil	65%	Yes
Water	35%	
Diolein* from tall oil	60%	No
Phosphatidicyl choline from soy	30%	
Water	10%	

5 * Purified by molecular distillation

CLAIMS

1. A biologically active composition, especially a
5 pharmaceutical composition, which is glycerol-ester-
based, c h a r a c t e r i s e d in that it contains

(a) at least one diacyl glycerol, wherein the acyl
groups, which are the same or different, are each derived
from an unsaturated fatty acid having 16-22, preferably
10 16-20, carbon atoms, or from a saturated fatty acid hav-
ing 8-10 carbon atoms,

(b) at least one phospholipid selected from glycerophosphatides and sphingophosphatides, wherein the acyl
groups, which are the same or different, are each derived
15 from a fatty acid having 14-22, preferably 16-20, carbon
atoms, and

optionally, (c) at least one polar liquid selected
from the group consisting of water, glycerol, ethylene
glycol and propylene glycol,

20 the proportions between the components (a), (b) and
optionally (c) being such that they together form an
L2-phase or a cubic liquid crystalline phase, wherein (c)
is an optional component in the case of L2-phase and a
requisite component in the case of cubic liquid crystal-
25 line phase, and the biologically active material being
dissolved or dispersed in said L2-phase or said cubic
liquid crystalline phase.

2. The composition as claimed in claim 1, c h a r -
a c t e r i s e d in that the fatty acid from which the
30 diacyl glycerol (a) is derived, is an unsaturated fatty
acid having 18 carbon atoms.

3. The composition as claimed in claim 1 or 2,
c h a r a c t e r i s e d in that the fatty acid from
which the phospholipid (b) is derived, is a fatty acid
35 having 16 or 18 carbon atoms, preferably a saturated
fatty acid having 16 carbon atoms or a monounsaturated
fatty acid having 18 carbon atoms.

17

4. The composition as claimed in claim 2 or 3, characterised in that the fatty acid is selected from the group consisting of oleic acid and linoleic acid, preferably oleic acid.

5 5. The composition as claimed in any one of the preceding claims, characterised in that the unsaturated fatty acid for the diacyl glycerol (a) is derived from an oil selected from the group consisting of canola, maize, cottonseed, olive, rape-seed, soybean, safflower,
10 sunflower, linseed and tall oil.

6. The composition as claimed in any one of the preceding claims, characterised in that the glycerophosphatide is selected from the group of lecithines and cephalines.

15 7. The composition as claimed in claim 6, characterised in that the glycerophosphatide is phosphatidyl choline.

8. The composition as claimed in any one of the preceding claims, characterised in that the
20 phospholipid is derived from soybean, rape-seed or yolk.

9. The composition as claimed in any one of claims 1-5, characterised in that the sphingophosphatide is sphingomyelin.

10. The composition as claimed in any one of the
25 preceding claims, characterised in that the polar liquid is water.

11. The composition as claimed in any one of the preceding claims, characterised in that the weight ratio of diacyl glycerol:phospholipid is in the
30 range from 95:5 to 50:50, preferably from 90:10 to 70:30.

12. The composition as claimed in any one of the preceding claims, characterised in that the weight content of the polar liquid (c), based on the total weight of (a) plus (b) plus (c), is in the range of
35 0-20 % by weight, especially 0-15 % by weight, such as 0-10 % by weight for the L2-phase and 5-15 % by weight for the cubic liquid crystalline phase.

13. The composition as claimed in any one of the preceding claims, wherein the proportions between the components (a), (b) and (c) are such that they form a cubic liquid crystalline phase, c h a r a c t e r i s e d
5 in that the cubic liquid crystalline phase is obtained by swelling of the corresponding L2-phase with the polar liquid selected from the group consisting of water, glycerol, ethylene glycol and propylene glycol.

14. The composition as claimed in any one of the preceding claims, c h a r a c t e r i s e d in that the
10 L2-phase and/or the cubic liquid crystalline phase is the phase (phases) as defined in the phase diagram in Fig. 1.

15. The composition as claimed in any one of the preceding claims, c h a r a c t e r i s e d in that the
15 biologically active material is selected from the group consisting of pharmaceutical compounds, such as antibiotics, antimycotics, proteins, peptides, steroids, local anesthetics, chemotherapeutants and antiviral substances.

20 16. The composition as claimed in any one of the preceding claims, c h a r a c t e r i s e d in that the biologically active material is present in an amount of 0.01-30 % by weight, based of the weight of the total composition, preferably 0.1-5 % by weight for soluble ma-
25 terials and 5-30 % by weight for a dispersion of said materials.

17. A method for preparing a biologically active composition as claimed in any one of claims 1-16, c h a r a c t e r i s e d by mixing the diacyl glycerol
30 (a), the phospholipid (b) and, optionally, the polar liquid (c) in such amounts that an L2-phase, alternatively a cubic liquid crystalline phase is formed, and dissolving or dispersing the biologically active material in the
L2-phase and/or the cubic liquid crystalline phase be-
35 fore, during or after the formation of said L2-phase or cubic phase.

19

18. The method as claimed in claim 17, c h a r -
a c t e r i s e d by forming the cubic liquid crystalline
phase in the position in which the controlled release of
the biologically active material is desired, by the pres-
5 ence or addition of the polar liquid (c) in said posi-
tion.

19. The method as claimed in claim 18, c h a r -
a c t e r i s e d in that the cubic liquid crystalline
phase is formed by the presence of body fluid.

10 20. Use of an L2-phase and/or a cubic liquid crys-
talline phase according to the definition in any one of
claims 1-16 for encapsulating a biologically active mate-
rial for obtaining a preparation, which yields a control-
led release of the biologically active material.


15 21. The use as claimed in claim 20 for preparing a
pharmaceutically acceptable preparation for administra-
tion of peptides/proteins.

22. The use as claimed in claim 20 for preparing a
pharmaceutically acceptable preparation for local treat-
20 ment on a mucous membrane.

23. The use as claimed in claim 20 for preparing a
pharmaceutically acceptable preparation for treatment of
paradontosis.

24. The use as claimed in claim 20 for preparing a
25 pharmaceutically acceptable preparation for administra-
tion of vaccines.

1/1

*Fig. 1*

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 95/00593

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: A61K 9/127, A61K 9/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EMBASE, MEDLINE, WPI, WPIL, CLAIMS, CA, JAPIO

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	Biochemistry, Volume 29, 1990, John M. Seddon, "An Inverse Face-Centered Cubic Phase Formed by Diacylglycerol-Phosphatidylcholine Mixtures" page 7997 --	1-24
A	WO 8402076 A1 (FLUIDCARBON INTERNATIONAL AB), 7 June 1984 (07.06.84) -- -----	1-24

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

3 October 1995

Date of mailing of the international search report

04 -10- 1995

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Anneli Jönsson

Telephone No. +46 8 782 25 00

28/08/95

PCT/SE 95/00593

Form PCT/ISA/210 (patent family annex) (July 1992)